



ISOLTECO RASATURA FIXATIVE

NEW

base surface

+ product:	Universal ready-to-use organic-based fixative.
+ packaging and storage:	<ul style="list-style-type: none"> ➤ tubs of 25 kg. ➤ pallet: 16 tubs = 400 kg ➤ storable for at least 6 months in a cool place away from frost. If not using up all the material, tightly seal the container after use.
+ composition:	Styrolacrylatic binder, silicone emulsion, mineral components, additives, water.
+ fields of application:	<p>Adhesive, substrate absorption power regulator, allowing a uniform colour of the finishing. For internal as well as external use.</p> <p>To be used before applying Silicate Coloured Isolteco Rasatura.</p>
+ consumption/yield:	about 300 g/m ²
+ surface preparation:	<p>The substrate must be clean, dry, free of dust and frost, hydroabsorbent, free of efflorescence, compact and resistant and fulfil what is required from the regulations ÖNORM B 2230 and ÖNORM B 3346.</p> <p>Recommended on:</p> <ul style="list-style-type: none"> ➤ smoothing plasters with scrim in any kind of thermal insulating systems; ➤ lime based, lime and cement based or cement based plasters applied with the float; ➤ concrete and other mineral surfaces; ➤ old plasters and mineral, silicate or resins based paintings that are well adherent to the wall surface; ➤ lime / gypsum, gypsum / lime or gypsum based plasters; ➤ plasterboard panels. <p>Not recommended on:</p> <ul style="list-style-type: none"> ➤ plastic materials and resins, lacquers and oil paintings, adhesives and dispersion colours; ➤ fresh lime based plasters. <p>Preliminary treatment of the wall and ceilings surface:</p> <ul style="list-style-type: none"> ➤ mechanically eliminate sandy surfaces and superficial films or, ➤ eliminate residues of products for the removing of the falsework on concrete with jets of hot water or specific products; ➤ mechanically clean or clean with jets of hot water surfaces which are dirty or with algas or musks, or apply specific products; ➤ mechanically eliminate mineral paintings which are deteriorated or with low adherence to the surface; ➤ apply a smoothing plaster on surfaces which are damaged or with cracks, by using, if necessary, even a scrim for reinforcement.
+ application:	<p>The surface must be compact and dry. Apply the product in a regular and uniform way on the whole surface. If necessary, repeat the operation (e.g. if the absorption capacity of the surface is not uniform), wait at least 24 hours after every application.</p> <p>Mix slowly with a suitable mixer.</p>

	<p>Do not add other products. The product can be applied with a roller or sprayed. Apply the product in a regular way and without interruptions. The right consistency can be reached by adding a minimum quantity of water.</p>
<p>+ warnings:</p>	<p>The temperature of the air, the material and the surface of application during the application and the setting phases must be higher than +5°C. Protect the facades from the direct sunlight, the rain and the strong wind (e.g. use the protective scrim for the scaffoldings). High humidity and low temperatures can considerably delay setting. Safety rules: especially protect glass, ceramic and clinker tiles, natural stone, lacquer and metal which may come into contact with the product. In case of splashing, wash abundantly with water. Do not wait until the product dries and sets. Clean the tools with water immediately after their use. Precautions: exempt from the obligation of classification S2 keep out from the children's reach S24 avoid contact with the skin S25 avoid contact with the eyes S37 wear protection gloves</p>
<p>+ technical characteristics:</p>	<ul style="list-style-type: none"> ➤ solid contents: about 62%. ➤ density: about 1.50 kg/dm³ ➤ pH value: 8.

All the indications provided in this technical data sheet are purely approximate and not binding for legal purposes. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation.

The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all the methods and instructions for use generally referable to "workmanlike" execution.

Edilteco S.p.A. reserves the right to change the contents of this technical data sheet on its final judgement.

Publication of this data sheet supersedes and cancels the validity of any other technical data sheet previously published.